

FILM  
INSERT  
HERE

Interior Side

### Benefits and selection criteria

- Shields >99% of UV radiation, helping to reduce fading of valuables, fabrics and furnishings\*\*
- Durable scratch-resistant coating for easy cleaning
- Reduction of hot spots helps increase HVAC efficiency and lower energy costs
- Used where both extremely high levels of heat and glare reduction are required, and a strong reflective gold appearance is a design specification



# FILM INSERT HERE

Exterior Side

## Performance Data

|   | % Total Solar Transmittance | % Total Solar Reflectance | % Total Solar Absorbance | % Visible Light Transmittance | % Visible Reflectance (exterior) | % Visible Reflectance (interior) | Winter U-value | Shading Coefficient | % Ultraviolet Ray Protection (wavelengths 300-380nm) | Emissivity | Solar Heat Gain Coefficient | % Total Solar Energy Rejected | Light-to-Solar Heat Gain Ratio (LSG) | % Summer Solar Heat Gain Reduction | % Winter Heat Loss Reduction | % Glare Reduction |
|---|-----------------------------|---------------------------|--------------------------|-------------------------------|----------------------------------|----------------------------------|----------------|---------------------|--|------------|-----------------------------|-------------------------------|--------------------------------------|------------------------------------|------------------------------|-------------------|
| Clear Glass<br>1/4" (6mm) single pane       | 77                          | 7                         | 16                       | 88                            | 8                                | 8                                | 1.03           | 0.94                | 38   | 0.84       | 0.82                        | 19                            | 1.07                                 | -                                  | -                            | -                 |
| Clear Glass<br>1/4" (6mm) dual pane         | 61                          | 11                        | 28                       | 79                            | 14                               | 14                               | 0.47           | 0.81                | 54   | 0.84       | 0.70                        | 30                            | 1.13                                 | -                                  | -                            | -                 |
| R15GO SR PS<br>1/4" (6mm) clear single pane | 9                           | 45                        | 46                       | 13                            | 50                               | 63                               | 0.91           | 0.25                | >99  | 0.62       | 0.22                        | 78                            | 0.59                                 | 73                                 | 12                           | 85                |
| R15GO SR PS<br>1/4" (6mm) clear dual pane   | 8                           | 35                        | 57                       | 12                            | 49                               | 63                               | 0.44           | 0.37                | >99  | 0.62       | 0.32                        | 68                            | 0.38                                 | 54                                 | 6                            | 85                |

The solar performance data reported for LLumar architectural window films was captured using the National Fenestration Rating Council's (NFRC) standard guidelines for window film solar performance measurement. All safety and performance data has been measured in accordance with ASTM, ASHRAE, AIMCAL and ANSI standards using NFRC methodology with Lawrence Berkeley National Lab's WINDOW Fenestration Analysis Software. Reported values are taken from representative product samples and are subject to normal manufacturing variances. Actual performance will vary based on a number of factors, including glass type and properties.